

**Amendments to the Specification:**

Please replace paragraphs [0037] and [0042], with the following rewritten paragraphs.

[0037] FIGURE 3, provides a cross sectional view of the present invention generally designated by reference to numeral 200 and includes a first layer or first sheet 210 and a second layer or second sheet 230. The curable coating ~~230~~ of the present invention is disposed between the first 210 and second 230 sheet of the laminated business form construction.

[0042] The production of the present invention is relatively straight forward and includes the provision of a first sheet of material, such as a translucent sheet of glassine or machine glazed or machine finished paper having a thickness ranging ~~form~~ from about 1 mil to about 3 mils. The UV curable coating is applied to the first sheet in a thickness ranging from about 0.001 mils to 3 mils with about 0.01 to 1 mils being preferred. Next, a top sheet is placed in registry and alignment with the bottom sheet so as to create an intermediate laminate, in which the sheets have not yet been bonded together.